

CORAL UNDERCOAT

(CSP 3)

Product description:

Type

A good quality, multi-purpose alkyd based undercoat, which provides a flexible, non-absorbent foundation for gloss finishes.

Features and benefits

Brushes deep into cracks, filling minor irregularities. Durable and has Good coverage, obliterating and sanding properties. It provides a sound base for the subsequent finishing coat.

Recommended use

Suitable for interiors and exteriors and can be used on all type soft surfaces, i.e. on wood, metal, plaster, stone, asbestos, etc. over the appropriate primer. Manufactured from pigments and extenders incorporated in a good quality alkyd resin.

Substrate

General-purpose primer for application on steel, galvanized steel and aluminum.

Product data:

Packaging size	1L and 4L
Colors	White
Finish, Dry Film	Smooth (Matt)
Solid by Volume	50-60 Volume% (Depends on Shade)
Specific gravity	1.20 ± 0.05
Viscosity	70 -80 KU
VOC Level	165-180g/L for white, pastel and medium colors. EPA Green seal standard is 200g/L for flat coatings
VOC comments	This is the theoretical value. Tested value will vary depending on test methodology, accuracy of equipment used for testing and test conditions.

Application data:

The product can be applied by

Brush, Roller : Recommended.

Spray Application: (refer to spray gun manufacturer's information)

- **Conventional gun** : Fluid Tip 1.3 – 1.6mm, Air pressure 50 psi (3.5 bar) at the gun
- **HVLP/Compliant gun** : Fluid Tip 1.2 – 1.5mm, Air pressure

Film thickness per coat

Typical recommended range

Theoretical Coverage: 8-10 m²/ liter

Film thickness will vary and is calculated as average.

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Maximum spread rate per coat is obtained at minimum dry film thickness.

Coral Undercoat

Thinner

Coral Solvents for Oil Paints T-100/Gloss Thinner

Dilution

Maximum 8-10 % by Volume for Spray Application

Special Remark

Do not apply un-recommended top coat on red oxide primer.
When applying Gloss on glossy surface the first coat should be lightly abraded with fine sandpaper to guarantee good inter-coat adhesion.

Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The drying time is measured by stated values	Relative Humidity (RH) 50 %
Substrate temperature	30 °C
Surface (touch) dry	4-5 hrs.
Hard dry	16-18 hrs.
Dry to over coat, minimum	Over night.

Directions for use:

Surface preparation

The substrate must be clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

Recommended paint system

- Coral Undercoat White : 1 Coat
- Coral Enamel Finish : 2 - 3 Coat

***It can change depending on Shade & Substrate.**

Coral Undercoat

Remarks:

Other systems may be specified, depending on area of use.

Masking tape has to be removed immediately after application of the topcoat.

Contents of packaging with different batch numbers must be mixed together before use. .

Storage:

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Environmental labelling:

Insignia Limited is an ISO 9001 and 14001 certified company for QMS and EMS respectively.

Refer to the product safety data sheet for more information.

Health and safety:

Ensure good ventilation during application and drying. Observe hygiene and safety regulations. Wash your hands carefully after painting. Avoid contact of paint with eyes and skin. Keep out of the reach of children. Do not use can/container to store food and water. Refer to Material Safety Data Sheet for additional safety information.

Disclaimer:

The information contained herein is to the best of our knowledge, accurate and current and is given in good faith without warranty. Users are deemed to have satisfied themselves independently as to the suitability of our products for their intended purpose. In no event shall insignia be liable for consequent or incidental damage.